











Granite	MOH Specifications					
	Density Kg/m3 (TR: ASTM C-97) 2560	Water Absorption % (TR: ASTM C-97)	Modulus of Rupture MPA (TR: ASTM C-99)	Flexural Strength MPA (TR: ASTM C-880)	Compressive Strength MPA (TR: ASTM C-170)	Abrasion Resistance
	Black Volcano					
	2869	0.02	19.5	24.7	160.1	33.2
	Najran Brown					
	2694	0.172	11	16.06	147.5	32.1
	Ancient Brown					
	2669	0.056	12.99	11.6	155.6	31
	Emerald Green					
	2659	0.052	15.6	12.4	151.9	27.1
	Golden Leaf					
	2662	0.23	14.4	14.1	158.8	32.1
	Golden Rose					
	2681	0.048	14	13.8	148.8	29.4
	Royal Gold					
	2680	0.141	13.5	10.6	138.6	29.7
	Royal Rose					
	2639	0.14	11.3	12.3	138.06	26.4
	Bianco					
	2656	0.15	12.55	10.86	139.5	29.7
	Pink					
	2646	0.281	11.3	10.8	170.9	28.9

Granite	MOH Specifications					
	Density Kg/m3 (TR: ASTM C-97) 2560	Water Absorption % (TR: ASTM C-97)	Modulus of Rupture MPA (TR: ASTM C-99)	Flexural Strength MPA (TR: ASTM C-880)	Compressive Strength MPA (TR: ASTM C-170)	Abrasion Resistance
	Silver Green					
	2667	0.068	12.2	14.2	129.3	26.7
	Sweet Gold					
	2625	0.07	13.06	14.9	153	29.5
	Violeta					
	2779	0.094	15.7	12.5	136.3	29.4
	White Pearl					
	2645	0.06	13.9	17.9	154.1	29.7
	Desert Gold					
	2618	1.02	10.3		77.4	18
	Desert Gray					
	2650.7	0.67	10		75.6	18
	Desert Yellow					
	2650.7	0.67	10		75.6	18
	Desert White					
	2618	1.02	10.3		77.4	18